

# EZ - KROM 30 R

## CLASSIFICATION

EN ISO 3581-A	AWS / ASME SFA-5.4
E 19 12 3 LR 12	E316L-16

## DESCRIPTION AND APPLICATION

A low-carbon rutile electrode for welding of identical and similar (stabilized and unstabilized) stainless steels. Weld metal is of austenitic Cr-Ni-Mo type with delta-ferrite. Weld metal is resistant to intergranular corrosion on working temperatures up to 350°C.

Steel grade	HRN	DIN (W. Nr.)	ASTM / AISI	EN / ISO
Stainless high-alloy austenite steels	Č 4573	X5 CrNiMo 17 12 2 (1.4401)	316	X5CrNiMo17-12-2
	Č 45703	X2 CrNiMo 17 13 2 (1.4404)	316 L	X2CrNiMo17-12-2
	Č 4574	X6 CrNiMoTi 17 12 2 (1.4571)	316 Ti	X6CrNiMoTi17-12-2
	Č 4583	X6 CrNiMoNb 17 12 2 (1.4580)	316 Cb	X6CrNiMoNb17-12-2
	ČL 4580	G-X6 CrNiMo 18 10 (1.4408)	-	GX5CrNiMo19-11-2
	ČL 4573	G-X10 CrNiMo 18 9 (1.4410)	-	-

## MECHANICAL PROPERTIES OF THE ALL-WELD METAL

R <sub>0.2</sub> N/mm <sup>2</sup>	R <sub>m</sub> N/mm <sup>2</sup>	A <sub>5</sub> %	KV (-20°C) J
> 320	> 510	> 25	> 47

## APPROXIMATE CHEMICAL COMPOSITION OF THE ALL-WELD METAL

	C	Mn	Si	Cr	Ni	Mo
%	≤ 0,03	0,9	0,8	18,5	12	2,7

## RECOMMENDED WELDING CURRENT


Ø mm	2,0	2,5	3,2	4,0	5,0
A	40 - 60	50 - 85	70 - 125	110 - 165	160 - 230

## PACKAGING

Electrode dimensions mm	Quantity per ton approx. pieces	Weight of packaging kg
Ø 2,0 x 300	79 100	1,1
Ø 2,5 x 300	52 800	1,1
Ø 3,2 x 350	26 300	1,1
Ø 4,0 x 350	18 200	1,2
Ø 5,0 x 350	9 100	6,0

## APPROVALS

ABS (316 L-16); BV (UP); DB; DNV (316 L); LR (316 L); RS (A-6); TÜV



Marking: **EZ - KROM 30 R**  
Dry before use 2h/300°C